

2-Sided Geocomposite

275mil Geonet



Geonet Component⁽⁴⁾

6-275-6

8-275-8

Property	Test Method	Minimum Average Roll Value ⁽⁵⁾	
Thickness, (mm)	ASTM D5199	275	275
*The thickness values may be changed due to project specifications (i.e., absolute minimum thickness)			
Peak Tensile Strength, lbs./in. (MD)	ASTM D5035	65	65
Melt Flow Index, g/10 minutes (max.)	ASTM D1238, 190°C, 2.16kg	≤1.0	≤1.0
Density, g/cm ³	ASTM D792, Method B	0.94	0.94
Carbon Black Content	ASTM D4218	2 - 3	2 - 3
Transmissivity ⁽¹⁾ , m ² /sec.	ASTM D4716	6 x 10 ⁻³	6 x 10 ⁻³

Geotextile Component (Prior to Lamination)

Property	Test Method	Minimum Average Roll Value ⁽⁵⁾	
Mass per Unit Area, oz./sq. yd.	ASTM D5261	6.0	8.0
Grab Tensile Strength, lbs.	ASTM D4632	170	225
Grab Elongation, %	ASTM D4632	50	50
Trapezoidal Tear, lbs.	ASTM D4533	70	90
Puncture, lbs.	ASTM D4833	95	140
Mullen Burst, psi	ASTM D3786	325	400
Permittivity ⁽²⁾ , sec. ⁻¹	ASTM D4491	1.60	1.26
Water Flow ⁽²⁾ , gpm./ft. ²	ASTM D4491	125	90
Apparent Opening Size, U.S. Std Sieve Size (max.)	ASTM D4751	70	80
UV Resistance after 500 hours, % Strength Retained	ASTM D4355	70	70

Geocomposite⁽⁴⁾

Property	Test Method	Minimum Average Roll Value ⁽⁵⁾	
Laminated Strength (Ply Adhesion), lbs./in.	ASTM D7005	1	1
Transmissivity ⁽³⁾ , m ² /sec.	ASTM D4716	7 x 10 ⁻⁴	7 x 10 ⁻⁴

Notes: (1) Geonet Transmissivity at a temp. of 21°C, gradient of 0.1 and a load of 10,000psf: seating time 15 min. between steel plates.

(2) At time of manufacture. Handling may change these properties.

(3) Geocomposite Transmissivity at a temp. of 21°C, gradient of 0.1 and a load of 10,000psf: seating time 15 min. between steel plates.

(4) Component Properties are prior to Lamination

(5) For Geonet, Melt Flow Index is a maximum value, and for Geotextile, AOS is a maximum average roll value.

(6) All roll lengths and widths have a tolerance of ±1%

All information, recommendations and suggestions appearing in this literature concerning the use of our products are based upon tests and data believed to be reliable; however, it is the users responsibility to determine the suitability for their own use of the products described herein. Since the actual use by others is beyond our control, no guarantee or warranty of any kind, expressed or implied, is made by Agru/America as to the effects of such use or the results to be obtained, nor does Agru/America assume any liability in connection herewith. Any statement made herein may not be absolutely complete since additional information may be necessary or desirable when particular or exceptional conditions or circumstances exist or because of applicable laws or government regulations. Nothing herein is to be construed as permission or as a recommendation to infringe any patent.